

Appln. No. 10/717,873
Amdt. dated 4-26-06
Reply to Office Action of February 2, 2006

BEST AVAILABLE COPY

Amendment to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- 1 (Currently amended) A synthetic cork closure for a liquid container having at least a portion thereof coated with a gas impermeable polymer wherein the coating is applied using a process selected from the group consisting of ~~analog gravure coating, offset coating, pad print coating, screen coating, stencil coating, brush coating, spray coating, pouring, painting, rolling, dipping, dripping~~ a composition containing the gas impermeable polymer onto the surface of the cork, and combinations thereof, wherein the gas impermeable polymer is dissolved in a solvent therefore and such that the resulting coating penetrates beyond the surface of the cork to an extent observable by light microscope when the coating is of a color different from that of the synthetic cork closure.
- 2 (Original) The synthetic cork closure of Claim 1 wherein only one end of the closure is coated with the gas impermeable polymer.
- 3 (Original) The synthetic cork closure of Claim 1 wherein both ends of the closure are coated with the gas impermeable polymer.
- 4 (Original) The synthetic cork closure of Claim 1 wherein the entire surface of the closure is coated with the gas impermeable polymer.
- 5 (Original) The synthetic cork closure of Claim 1 wherein the gas impermeable polymer is a vinylidene chloride polymer.
- 6 (Original) The synthetic cork closure of Claim 5 wherein the vinylidene chloride polymer is (1) a copolymer of (a) from about 80 to about 93 mole percent vinylidene chloride and (b) from about 20 to about 7 mole percent of at least one monoethylenically unsaturated monomer copolymerizable therewith or (2) a copolymer of (a) from about 65 to about 75 mole percent vinylidene chloride and (b) from about 35 to about 25 mole percent of at least one monoethylenically unsaturated monomer copolymerizable therewith.
- 7 (Original) The synthetic cork closure of Claim 6 wherein the closure is coated using a process which comprises a process selected from the group consisting of painting, rolling, dipping, dripping, pouring the composition containing the gas impermeable polymer onto the surface of the cork and combinations thereof.
- 8 (Original) The synthetic cork closure of Claim 6 wherein the closure is coated using a process which comprises a process selected from the group consisting of analog gravure

60665B

Page 2 of 24

Appln. No. 10/717,873
Amdt. dated 4-26-06
Reply to Office Action of February 2, 2006

BEST AVAILABLE COPY

coating, offset coating, pad print coating, screen coating, stencil coating, brush coating, spray coating, and combinations thereof.

- 9 (Original) The synthetic cork closure of Claim 1 wherein the closure is coated using a process which comprises inserting a synthetic cork closure into a container, applying onto the free end of the synthetic cork closure a coating composition comprising a vinylidene chloride polymer dissolved in a solvent and allowing the solvent to evaporate.
- 10 (Original) The synthetic cork closure of Claim 1 wherein the closure is coated using a gas impermeable polymer coating composition comprising from about 5 weight percent to about 20 weight percent of a vinylidene chloride polymer, from about 70 weight percent to about 90 weight percent of an organic solvent or blend of organic solvents and from about 5 weight percent to about 10 weight percent of a thixotropic agent.
- 11 (Previously presented) The synthetic cork closure of Claim 10 wherein the organic solvent is selected from the group consisting of acetone, methyl ethyl ketone, cyclohexanone, ethyl acetate, n-propyl acetate, isopropyl acetate, dibutyl ether, propylene oxide, dioxane, toluene, tetrahydrofuran and mixtures thereof.
- 12 (Original) The synthetic cork closure of Claim 10 wherein the thixotropic agent is selected from fumed silica, kaopolite, bentonite, talc and mixtures thereof.
- 13 (Original) The synthetic cork closure of Claim 10 wherein the blend of organic solvents comprises at least one solvent selected from the group consisting of acetone, methyl ethyl ketone, cyclohexanone, ethyl acetate, n-propyl acetate, isopropyl acetate, dibutyl ether, propylene oxide, dioxane, toluene, tetrahydrofuran and mixtures thereof and at least one cosolvent selected from the group consisting of aliphatic and alicyclic hydrocarbons and dialkylethers.